

### III. SAMPLES TRACEABILITY

#### III.1. M 1194

Sample M 1194 was received in a container and laid on the ground by the transporter. Prior to the tests, sample M 1194 has been screened at 200 mm and bagged, the coarser blocks being crushed by hand with a hammer. In order to avoid natural drying, this operation was achieved as soon as possible after sample reception. Pictures 1 to 4 show, respectively, the bagging installation, the size of some coarsest aggregates, the screening operation and the hand crushing.

Picture 1 : Bagging installation - overall view.



Picture 2 : Coarsest aggregates (size of the reference stick : 200 mm).

